



**MAX  
245°C**

**MSL  
1**

PRODUCT FAMILY	Material	CAS Number	% Normalize for BOM	Wt. Of BOM Item (g)	% by Wt (Comp. Item)	mg/unit	% by Wt Of Unit	ppm
<b>752 8 SRT</b>							<b>180.70</b>	
Alumina Ceramic	Al2O3	1344-28-1	0.8800	0.1590	87.50%	139.1390	77.00%	770000
	SiO2 (silicon dioxide)	14808-60-7			12.50%	19.8770	11.00%	110000
					<b>100.00%</b>	<b>159.0160</b>		
Conductor Thick Film	Ag	7440-22-4	0.0068	0.0012	99.00%	1.2165	0.67%	6732
	Pd	7440-05-3			1.00%	0.0123	0.01%	68
					<b>100.00%</b>	<b>1.2288</b>		
Resistor Thick Film	RuO2	12036-10-1	0.0079	0.0014	30.00%	0.4283	0.24%	2370
	PbO	1317-36-8			10.00%	0.1428	0.08%	790
	SiO2 (silicon dioxide)	14808-60-7			30.00%	0.4283	0.24%	2370
	B2O3	1303-86-2			30.00%	0.4283	0.24%	2370
					<b>100.00%</b>	<b>1.4275</b>		
Notch Conductor Thick Film	Ag	7440-22-4	0.0113	0.0020	99.00%	2.0215	1.12%	11187
	Pd	7440-05-3			1.00%	0.0204	0.01%	113
					<b>100.00%</b>	<b>2.0419</b>		
Underplate	Ni	7440-02-0	0.025	0.0045	100.00%	4.5175	2.50%	25000
					<b>100.00%</b>	<b>4.5175</b>		
Finish Plate	Sn	7440-31-5	0.017	0.0031	90.00%	2.7647	1.53%	15300
	Pb	7439-92-1			10.00%	0.3072	0.17%	1700
					<b>100.00%</b>	<b>3.0719</b>		
Covercoat	TiO2	13463-67-7	0.0520	0.0094	50.00%	4.6982	2.60%	26000
	Silicone	218163-11-2			50.00%	4.6982	2.60%	26000
		Sum		1.0000 part weight	0.1807	<b>100.00%</b>	<b>9.3964</b>	
		<b>Totals:</b>		<b>0.1807</b>		<b>180.70</b>	<b>100.00%</b>	<b>1000000</b>